



## DATA SHEET

## FUSED QUARTZ VITREOSIL® 077

### Vitreosil® 077 Optical Fused Quartz

Vitreosil® 077 optical fused quartz is manufactured by flame fusion of naturally occurring high-purity quartz crystal. Vitreosil® 077 has a useful transmission range from <260 nm in the near UV through to >2 000 nm in the infrared.

\* The optical properties of re-drawn rod and tube are not as shown in the table below

Vitreosil® 077 high-purity fused quartz has a useful transmission range from <260 nm in the UV to >2 000 nm in the infrared

### Optical Properties Typical Chemical Analysis

Vitreosil® Grade	077
<b>Bubbles</b>	
Bubble class (DIN 58927)	0..1
Sum of CSA (mm <sup>2</sup> / 100 cm <sup>3</sup> )	< 0.1
Maximum bubble diameter (mm)	0.5
<b>Maximum number of inclusions</b> (0.1 - 0.2 mm per 100 cm <sup>3</sup> ) (Bubbles and inclusions < 0.1 mm are not counted)	2
<b>Striae</b> (MIL-G-174A) in functional direction (i.e. direction of view) (The direction of view should be specified at time of enquiry / order)	B
<b>Granularity</b>	Faint
<b>Residual strain</b> (nm/cm)	< 5
<b>Fluorescence</b> (254 nm excitation)	Blue / Violet
<b>Radiation resistance</b>	
UV	Slight darkening after prolonged exposure
X-Ray & Gamma Ray	Darkens after 10 <sup>7</sup> RAD

Vitreosil®077	
Typical trace elements in ppm †	
<b>Al</b>	15
<b>Ca</b>	0.5
<b>Cr</b>	< 0.01
<b>Cu</b>	< 0.01
<b>Fe</b>	0.1
<b>K</b>	0.2
<b>Li</b>	0.2
<b>Mn</b>	0.01
<b>Na</b>	0.1
<b>Nd</b>	0.01
<b>Ti</b>	1.3
<b>Y</b>	< 0.1
<b>Zr</b>	1.3
<b>OH</b>	170

† Chemical analysis can vary slightly between individual batches of material

## Thermal Data


Strain Point ‡ 1085oC  
Annealing Point ‡ 1195oC  
Softening Point ‡ 1730oC

Thermal Expansion  
Coefficient (Average)  $0.54 \times 10^{-6}$

‡ Note that these values may vary, depending on the thermal history of the glass

## Transmission

Typical external transmission of Vitreosil® 077 fused quartz (including Fresnel reflection losses for 10 mm pathlength)



WHILE EVERY ATTEMPT HAS BEEN MADE TO VERIFY THE SOURCE OF THE INFORMATION, NO RESPONSIBILITY IS ACCEPTED FOR ACCURACY OF DATA.

**UQG LTD, THE NORMAN INDUSTRIAL ESTATE, 99-101 CAMBRIDGE ROAD,  
MILTON, CAMBRIDGE, CB4 6AT, ENGLAND. TEL: +44 (0) 1223 420329 FAX: +44  
(0) 1223 420506**